

Enamel Frit




TOMATEC(XIAMEN) FINE MATERIAL CO., LTD.

361023 Guankou Sanshe, Jimei, Xiamen, Fujian

TEL : (86) 0592-6385552

FAX : (86) 0592-6385553

Frit NO.	Type	Fusion F. [mm]	C.O.E [x10-7/oC]	Firing Temp.[oC]	Color	Acid Resistance	Uses
TMG - 018	GC Hard	21	276	880	Brown	---	Normal
TMG - 031	GC Hard	25	281	880	Blue	---	Liberty
TMG - 035	GC Medium Hard	37	310	860	D.Gray	---	Normal
TMG - 050	GC Medium	46	323	830	Blue	---	Liberty
TMG - 070	GC Medium	42	324	830	D.Gray	---	Liberty
TMG - 094	GC Soft	120	352	780	D.Gray	---	Liberty
TMG - 112	GC Soft	84	348	780	Blue	---	Liberty
TMW - 130	CC Ti - White	31	288	820	White	A	Cook ware
TMW - 150	CC Ti - White	34	285	820	White	A	Cook ware
TMW - 155	CC Ti - White	26	270	820	White	AA	Cook ware
TMW - 170	CC Ti - White for D/on	33	281	820	White	A	Cook ware/Panel
TMW - 230	CC Ti - White for Cast iron	47	331	780	White	A	Cook ware
TMW - 955M	CC Ti - White for Cast iron	---	323	900	White	AA	Dry process
TMT - 250	CC Transparent	33	325	820	---	A	Cook ware/Panel
TMT - 255	CC Transparent	35	354	800	---	B	Cook ware/Panel
TMT - 260	CC Transparent	56	330	800	---	A+	Cook ware/Panel
TMT - 265	CC Transparent	57	355	780	---	B	Cook ware/Panel
TMT - 270	CC Transparent	29	292	830	---	A+	Cook ware/Panel
TMT - 290	CC Transparent for Metallic	22	309	830	---	AA	Cook ware/Panel
TMT - 310	CC Semi Opaque	30	281	820	---	A	Cook ware/Panel
TRA - 360	GC Acid/Hot water Resistant	53	350	840	Blue	AA	Cook ware
TRA - 370	GC Acid/Hot water Resistant	42	311	830	Blue	AA	Cook ware
TRA - 380	GC Acid Resistance	46	321	830	Black	A	Cook ware
TRA - 390	GC Acid Resistance	44	310	820	Black	A	Cook ware
TMC - 410	CC For cast iron	44	303	780	Black	A	Cast-Iron
TMC - 413	CC For cast iron	39	303	780	Tsansp	A	Cast-Iron
TMC - 415	GC For cast iron	37	313	780	Black	A	Cast-Iron
TMC - 435	GC For cast iron	---	371	780	---	A	Cast-Iron
TMC - 450	GC Compound for cast iron	---	---	780	---	---	Cast-Iron
TMC - 460	GC Compound for cast iron	---	---	830	Black	---	Cast-Iron
TMC - 470	Matt Compound for cast iron	---	---	780	Black	A	Cast-Iron
TMS - 497	CC For Aluminum	---	520	550	Tsansp	A	---
TMS - 500	CC For speckle	20	267	850	White	A	---
TMS - 510	CC For Dutch marble	---	333	820	White	---	Cook ware/Panel
TMS - 530	CC For mirror finish	---	252	800	Brown	A	---
TMS - 540	CC Majolica	50	335	770	Burgundy	A	Cast-Iron
TMS - 560	CC Majolica	45	320	770	Atrovirens	A	Cast-Iron
TMS - 580	CC Majolica	39	325	770	Blue	A	Cast-Iron
TMS - 600	CC Majolica	43	330	770	Brown	A	Cast-Iron
TMS - 535	CC Titanium Matt	26	386	800	---	---	---
TMP - 550	CC Smelt-in color	45	320	820	Ivory	A	Cook ware
TMP - 570	CC Smelt-in color	32	280	830	Ivory	A	Cook ware/Panel
TMP - 690	CC Smelt-in color	29	288	820	Ivory	A	Cook ware
TMP - 770	CC Smelt-in color	34	285	820	Yellow	A	Cook ware
41002T	GC Electrostatic powder	---	330	830	Black	A	Barbecue/Oven
41006	GC Electrostatic powder	---	325	830	Black	A	Barbecue/Oven
41009	GC Electrostatic powder(2C1F)	---	325	820	Black	A	Barbecue/Oven/Panel
41010	GC Electrostatic powder	---	330	830	Black	A	Barbecue/Oven
41022	GC Electrostatic powder	---	330	840	Blue	AA	Heat Exchange Panel
31200	CC Ready to use	---	---	800	Tsansp	AA	Cook ware
31201	CC Ready to use KIRA	---	---	800	Silver	AA	Cook ware
31202	CC Ready to use KIRA	---	---	800	Gold	AA	Cook ware
31021	GC Ready to use	---	---	840	Blue	AA	Hot-water tank
31032	GC Ready to use	---	---	830	Gray-Blue	---	Normal GC
31050	GC Ready to use	---	---	830	Black	A	For common use
31054	GC Ready to use	---	---	850	Black	AA	For common use
31055	Matt Teflon under coat	---	---	800	Gray	---	Cook ware
31069	CC Easy to Clean SARA	---	---	820	Black	AA	Cook ware
31077	GC Matt finish	---	---	840	Black	---	Cook ware
31089	Matt Co/Ni Free	---	---	770	Black	A	Compound for Cast-Iron