

# Glaze Frit



TOMATEC(XIAMEN) FINE MATERIAL CO., LTD.  
361023 Guankou Sanshe, Jimei, Xiamen, China

TEL: (86) 592-3133111

FAX: (86) 592-6385553

Frit NO.	Type	Firing Temperature [°C]	C.O.E [x10 <sup>-7</sup> /°C]	D.S.P [°C]	Uses
11 - 3841	Zircon Opaque	1080-1150	182	670	Wall Tiles
11 - 3870	Zircon Opaque	1120-1170	180	785	Wall Tiles
12 - 3614	Transparent	1000-1100	198	640	Dolomite China
12 - 3725	Transparent	1120-1170	185	710	Vitrious China
12 - 3730	Transparent	1050-1120	188	630	Dolomite China
12 - 3737	Transparent	1050-1120	165	575	Bone China
12 - 3795	Transparent	1100-1150	205	625	Bone China
12 - 3798	Transparent	1050-1120	212	663	Dolomite China
12 - 3979	Transparent	1100-1150	174	700	Vitrious China
CFT-014	Transparent	1100-1150	252	650	Bone China
CFT-015	Transparent	1100-1150	209	691	Magnesia Porcelain
14 - 3661	Matt	1100-1200	36	-	Low C.O.E. Matt
14 - 3663	Matt	1100-1200	80	-	Low C.O.E. Matt

# Bone China Glaze

Product NO.	Type	Firing Temperature	C.O.E [x10 <sup>-7</sup> /°C]	D.S.P [°C]	Uses
MG-503MX	Transparent	1120-1160	230	645	Bone China
BC-505MX	Transparent	1120-1160	231	670	Bone China
BC-507MX	Transparent	1120-1160	224	650	Bone China
BC-622MX	Transparent	1120-1160	221	673	Bone China